

# Dazzle Trans Finishing Sheet

## APPLICATION INSTRUCTIONS

GLOSS FINISHING SHEET SKU DAZZLE-TRANS



350°- 375°



5-10 Seconds



Medium Pressure  
40-60 PSI



Cold Peel

### PRESSING INSTRUCTIONS

Set your heat press to 350-375 F°

Position the garment with the already transferred image on the heat press as you would normally

Place the sheet of Dazzle-Trans, shiny side down, over the top of the image so that it covers the entire transfer area.

Using the above-recommended temperature, apply medium-firm pressure for 5-10 seconds

Open the press and begin rubbing the back of the transfer with a soft cloth. You may remove the garment at this time, however, do not peel the Dazzle-Trans yet.

When the sheet is completely cold, you may peel it away carefully.

### TIPS & TRICKS

If the transfer paper is sticking, it is possible that the Dazzle Trans has not cooled enough or has been left on the heat press for too long. Reduce temperature and/or time and repeat.

Leave finished garment for at least 24 hours before washing.

Fabrics may be machine washed (inside out, with like colors) in cold water.

Dry at normal setting; do not dry clean.

Keep product in closed package between uses; store in a cool, dry place.